

## TRI- TILE FG

Epoxy mortar for tile fixing and grouting.

### Description

Tri-Tile FG is a three component solvent free mortar comprising part A and Part B and selected filler (part c). The three components after mixing will reach a consistency which gives excellent bedding, troweling and gunning properties.



### Uses

Chemical resistance mortar designed for pointing between acid resistance bricks and somaga tiles. It is used in sewers, culverts, manholes and related structure.

### Advantages

- Chemical resistance: unaffected by a wide range of acides, alkalis and industrial chemicals.
- Ease of application: it is formulated to allow application by trowel or knife.
- High bond strength: has a good chemical and physical bond to all substrate including bricks and tiles.
- Highly resistance for high concentration of acids.
- Long pot life: allow for long working time.
- Solvent free: so it is low hazards.

### Technical Data @°25c

Color	White - other colors under request.
Density	1.8 kg / L
Setting time	45 - 60 min @ 25 C
Compressive strength	70 N/mm <sup>2</sup> after 7 days
Mixing Ratio	4A : 1 B : 10 C
Rate of use (theoretical)	As a tile adhesive : 7 - 8 kg per m <sup>2</sup>
	As a grouting : according to joint dimensions (L = 1.8 Kg)
<b>Chemical resistance</b>	
Bleach	Excellent
Detergent	Excellent
Saturated sugar	Excellent

#### Factory & Head Office:

6 October City - 4th Industrial Zone - Al Oula Industrial Zone Plot No.: 14  
 Tel.: (002) 011 195 48267 - Sales: (002) 010 007 88817 - (002) 011 184 87597  
 Technical Support Call : (002) 011 184 87880 - Email: sales@tichem-eg.com

## **TRI- TILE FG**

**Epoxy mortar for tile fixing and grouting.**

### **Directions for use**

#### **Surface preparation**

The surface should be clean, sound and free of dirt, dust, grease and oil.  
The material can be applied to either dry or moist surface however any free standing water should be removed prior to application.

#### **Mixing**

**Tri-Tile FG** is supplied in per-measured components. To mix, stir liquid components individually then pour into a clean pail, mix thoroughly with a hand mixer until uniform consistency has been reached, slowly mix the powder filler into the premixed liquid until a uniform consistency is achieved.

#### **Application**

Can be applied either by pointing trowel or using a hand gun or knife.  
The joint should be slightly overfilled and tool to obtain a smooth dense finish.

#### **Note:**

The epoxy compound should be applied only when the substrate temperature and ambient temperature is above 5°C

---

### **Cleaning**

Clean equipment with thinner.

---

### **Package**

Pack -6 kg

---

### **Storage**

Should be stored in original closed container, avoid the direct sun light, moisture.  
The storage temperatures (10 – 30) C° t.

---

### **Shelf life**

Has a shelf life of 24 months stored in dry and cool place

---

### **Health and safety**

Should not come in contact with skin and eyes or be swallowed.  
Avoid prolonged inhalation of solvent vapours.  
Some people are sensitive to epoxy resins, hardeners and solvents. Gloves, goggles and a barrier cream such as should be used.  
Ensure adequate ventilation and if working in enclosed areas use suitable breathing apparatus.  
If mixed resin comes into contact with the skin, it must be removed before it hardens with a resin removing cream followed by washing with soap and water. Do not use solvent.  
If accidental eye contamination occurs with any of the above products, wash well with plenty of clean water and seek medical advice.

**page 2 of 2**



#### **Factory & Head Office:**

6 October City - 4th Industrial Zone - Al Oula Industrial Zone Plot No.: 14  
Tel.: (002) 011 195 48267 - Sales: (002) 010 007 88817 - (002) 011 184 87597  
Technical Support Call : (002) 011 184 87880 - Email: sales@tichem-eg.com

www.trichem-eg.com