

TRI- HARD TOP

Surface hardening compound for fresh concrete floors

Description

Tri-Hard Top surface hardening compound is a quality controlled, factory Blended powder which is ready to use on site. It consists of hard wearing aggregates selected for their physical properties of abrasion and wear Resistance, Portland cement and special additives to improve workability. This combination produces a material which is easy to trowel in the surface of fresh, wet concrete.

Tri-Hard Top cures monolithically to provide a dense non porous surface which is extremely hard wearing and abrasion resistant.

Tri-Hard Top available in natural (concrete Grey) color as standard. special Colors, including Brick Red, Green and off white can be produced on request For large orders.

The product is certified by (National Research Centre)



Design criteria

The base concrete should have a minimum cement content of 300 Kg/m³. The concrete mix should be designed to minimize segregation and control bleeding , although some limited bleed is desirable to ensure sufficient moisture is available to wet out **Tri-Hard Top** when it is first applied. the use of water reducing admixtures from **Tri-Mix** range is strongly recommended in order to achieve water /cement ratio below 0.55.

Uses

Tri-Hard Top provides a highly abrasion resistance surface to fresh concrete floors by the dry shake method which ensure that hard wearing surface bonds monolithically to the base concrete .It is ideally suited for all industrial areas subjected to heavy traffic, e.g. power stations, agricultural buildings, distillation plants , laboratories , warehouse floors , work shops and all production areas.

Advantages

- Supplied ready to use - no additive required.
- Provides a hard abrasion resistant surface.
- Forms monolithic bond with fresh concrete.
- Hard, dense surface resistant to oil and grease.
- Available in range of colors to improve working environment.
- Non metallic aggregates - will not rust when wet.

page 1 of 3



Factory & Head Office:

6 October City - 4th Industrial Zone - Al Oula Industrial Zone Plot No.: 14
Tel.: (002) 011 195 48267 - Sales: (002) 010 007 88817 - (002) 011 184 87597
Technical Support Call : (002) 011 184 87880 - Email: sales@tichem-eg.com

www.trichem-eg.com

TRI- HARD TOP

Surface hardening compound for fresh concrete floors

Technical Data @°25c

| DESCRIPTION | VALUE |
|--|---|
| Appearance | Concrete color (Grey)- Brick Red - Green. |
| Base | Cement , additives and special aggregates |
| Abrasion resistance ASTM D4060 | 179.3 mg loss in weight |
| Abrasion resistance for concrete surface | Approx. 200 % |
| Rate of use | 3 Kg/m ² for light traffic 5 Kg/m ² for medium traffic to heavy traffic. |

Derictions for use

Tri-Hard Top should be applied at even application rate of 3 - 5 Kg/ m². It is recommended that the floor be marked off into bays of known area. Sufficient materials should then be laid out to meet the recommended spread rate

Application of **Tri-Hard Top** should begin without delay when the base concrete Has stiffened to the point light foot traffic leaves an imprint. Any bleed water Should now have evaporated, but the concrete should have a wet sheen. In large floors it will be necessary to work progressively behind the laying team to Ensure application at the correct time.

Tri-Hard Top is applied in two stages:-

(1) The first application is broad cast at an even rate of 3 Kg/ m² onto the Concrete surface. When the material becomes uniformly dark by the absorption Of moisture from the base concrete, this first application can be floated . Wooden floats, or on large areas, a power may be used.

It is important however, that the surface is not overworked.

(2) Immediately after floating, the remaining 2 Kg/ m² of **Tri-Hard Top** are applied Evenly over the surface at right angle to the first. Again, when moisture has been Absorbed the surface can be floated in the same way as before.

Final finishing of the floor using the plates of the power float can be carried out When the floor has stiffened sufficiently so that damage will not be caused. any addition of water tower out the surface on either the first or second application Of **Tri-Hard Top** will be detrimental to the overall quality of the floor.

Curing

Proper curing of concrete floors treated with **Tri-Hard Top** is essential to the physical properties of the finished floor.

The most effective method of curing is to use **Tri-Cure** which should be applied on the finished floor 10 minutes after the power floating operation has been completed.

page 2 of 3



Factory & Head Office:

6 October City - 4th Industrial Zone - Al Oula Industrial Zone Plot No.: 14
Tel.: (002) 011 195 48267 - Sales: (002) 010 007 88817 - (002) 011 184 87597
Technical Support Call : (002) 011 184 87880 - Email: sales@tichem-eg.com

www.trichem-eg.com

TRI- HARD TOP

Surface hardening compound for fresh concrete floors

Cleaning

Clean all equipments with water immediately after use. Hardened materials can be removed mechanically only.

Package

25 Kg bag

Shelf Life

The shelf life of the product is 24 months in unopened condition if stored as Per the recommendations.

Exposure to high temperature and humidity will result in considerable Deterioration of the product and reduce its shelf life.

Storage

Store the material in a cool, covered dry place. Do not expose the pails to direct sunlight and keep away from all sources of heat.

Health and Safety

As with all construction chemical products, caution should always be exercised. Protective clothing such as rubber gloves, safety goggles and face mask should Be worn when handling the product. Treat any splashes to the skin or eyes with copious amount of fresh water.

Should any of the products be accidentally swallowed, do not induce vomiting but ask for medical assistance immediately.



Factory & Head Office:

6 October City - 4th Industrial Zone - Al Oula Industrial Zone Plot No.: 14
Tel.: (002) 011 195 48267 - Sales: (002) 010 007 88817 - (002) 011 184 87597
Technical Support Call : (002) 011 184 87880 - Email: sales@tichem-eg.com

www.trichem-eg.com